



Maxeta 10


SMAW - (Stick) - MMA
Un-alloyed

Date: 2013-10-21
Revision: 22

Description:

Maxeta 10 is rutile-coated iron powder electrode with 135% recovery intended for welding medium thick sections in general construction steels. The electrode design has been optimised to produce fillet welds with a good mitre profile and throat thickness in the 3.5-4.0 mm range. Maxeta 10 produces a finely rippled bead surface, minimum spatter and a self-detaching slag.

Welding positions:



Coating type:

Rutile

Welding current:

DC+/-, AC OCV ≥ 65 V

Metal recovery:

135%

Redrying temperature:

90 °C, 2h

Chemical composition, wt.%

	C	Si	Mn	P	S	Cr	Ni
Min		0,40	0,40				
Typical	0,07	0,7	0,6	0,02	0,01		
Max	0,10	0,80	0,80	0,030	0,020	0,1	0,2

	Mo	Cu	V	Nb
Min				
Typical				
Max	0,1	0,2	0,05	0,05

Mechanical properties

	<u>Specified</u>	<u>Typical</u>
Yield strength, Re:	≥420 MPa	470 MPa
Tensile Strength, Rm:	510-610 MPa	570 MPa
Elongation, A5	≥ 22%	24%
Impact energy, CV:	0 °C • ≥47 J	0 °C • 50 J

Classification:

EN ISO 2560-A E 42 0 RR 53
AWS A5.1 E 7024

Approvals:

GL 2Y
CE
ABS 2
BV 2, 2Y
DNV 2
LR 2m, 2Ym

Produkt data:

Diam.mm	Length mm	Product code	Current A	Voltage V	Kg weld metal/ kg electrodes	No. of electrodes/ kg weld metal	Kg weld metal/ hour arc time	Burn-off time/ electrode (sec.)
2,5	350	72022500	90-125	28	0,7	45	1,6	46
3,2	450	72023200	130-160	29	0,73	23	2,2	61
4,0	450	72024000	140-220	30	0,65	17	2,6	73
4,5	600	72024560	160-230	29	0,70	10	2,9	130
5,0	450	72025000	190-310	31	0,66	11	3,7	78