



# Elgaloy Hard 100

REPAIR & MAINTENANCE  
Other

Date: 10/10/2018  
Revision: 17

## Description:

Elgaloy Hard 100 is a high recovery electrode, producing a weld metal deposit extremely rich in chromium carbides which is highly resistant to abrasion but exhibits limited impact resistance. Ideal for hardsurfacing components used in the mining and quarrying industries. Good wear and corrosion resistance at elevated temperatures. Surface cracking is normal and can be reduced by preheating to 250-450 °C. A buffer layer of Elgaloy Mix 18 is recommended for heavy build-ups or surfacing 13% Mn steels to prevent crack propagation into base material. Deposits are not machinable but can be ground.


## Guide for usage:

The electrode is preferably to be used with DC+, to create a thick build up also AC is possible to use.

## Applications:

Excavator teeth, dredger bucket lips, sizing screens, rollers, screw conveyors, scraper and mixer blades, crusher jaws and hammers, chutes, agriculture implements, rolling mill guides sinter plant.

## Welding positions:



## Coating type:

Special

## Metal recovery:

175 %

## Redrying temperature:

350 °C, 2h

## Hardness as welded:

58-61 HRC, 700 - 740 HV10

## Welding current:

DC+, (AC)

## Chemical composition, wt. %

	C	Cr	Mo	V
Min	3,0	29,0	0,45	0,30
Typical	3,5	30	0,5	0,4
Max	4,5	32,0	0,6	0,50

## Classification:

EN 14700

E Fe14

## Approvals:

## Product data:

Dim.mm	Current A
3,2x350	115-140
4,0x450	140-190