

MEGAFIL[®] 735 B



AWS A5.29: E80T5-G H4

EN ISO 17634-A: T Mo B M21 3 H5

WELDING POSITIONS:



FEATURES	BENEFITS	APPLICATIONS
<ul style="list-style-type: none"> Extremely low diffusible hydrogen weld deposit Extremely clean weld puddle Ideal for repair welding Low spatter loss Easy slag removal 	<ul style="list-style-type: none"> Minimizes risk of hydrogen-induced cracking High reserve of toughness and crack resistance High flexibility No additives needed Reduced cleaning time 	<ul style="list-style-type: none"> Steel construction Mechanical engineering Vessels (Mo steels up to 500 °C (932 °F)) Pipelines Single and multi-pass welding

WIRE TYPE	Gas shielded basic flux-cored wire
SHIELDING GAS	75-85% Argon (Ar) / Balance Carbon Dioxid (CO ₂); Gas Flow 12-18 l/min (25-38 cfh)
TYPE OF CURRENT	Direct Current Electrode Positive (DCEP)
STANDARD DIAMETERS	Ø 1.2 - 1.6 mm (0.045 - 1/16")
TYPICAL DIFFUSIBLE HYDROGEN*	< 3.0 ml / 100 g; Guaranteed for the total processing time < 4.0 ml / 100 g maximum (AWS Spec)
RE-DRYING	Not required due to seamless wire design.
STORAGE	The same conditions as for solid wire. Product should be stored in a dry, enclosed environment, in its original undamaged packaging

*Measurement technique is the carrier gas method according to AWS and ISO

MATERIALS TO BE WELDED*

Boiler steels	Rel ≤ 355 MPa	P235GH - P355GH, 16Mo3
Pipe steels	Rel ≤ 460 MPa	P235T1/T2 - P460NL1, L210 - L415MB
Fine grain structural steels	Rel ≤ 460 MPa	S255 - S460QL

*) The specified base materials are not complete and should only be seen as examples. The selection of the appropriate combination of steel and welding consumable should follow the specific mechanical strength and toughness requirements

ALL WELD METAL CHEMISTRY (%) (typical values for mixed gas 82% Ar / 18% CO₂)

Carbon (C)	0.07	Nickel (Ni)	-
Manganese (Mn)	1.1	Molybdenum (Mo)	0.5
Silicon (Si)	0.3	Chromium (Cr)	-
Sulphur (S)	0.015		
Phosphorus (P)	0.015		

ALL WELD METAL MECHANICAL PROPERTIES (for mixed gas 82% Ar / 18% CO₂)

Mechanical tests	Typical values MPa (ksi)	ISO Specification MPa (ksi)
Tensile Strength Rm	600 (87)	550 - 680 (80 - 99)
Yield strength Rp0.2	520 (75)	> 470 (68)
Expansion A5	26%	22%

The specified values apply to the stress-relieved condition (600 °C / 60 min)

CHARPY V-NOTCH IMPACT VALUES (for mixed gas 82% Ar / 18% CO₂)

Mechanical Tests	Typical values [J] (ft.lbf)	ISO Specification [J] (ft.lbf)
-20 °C	140 (103)	> 47 (35)
-40 °C	120 (89)	> 47 (35)

The specified values apply to the stress-relieved condition (600 °C / 60 min)

APPROVALS: CE, TÜV

Please contact the manufacturer to learn the present scope of approvals

The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and ITW Welding GmbH expressly disclaims any liability incurred from any reliance thereon. Typical data are those obtained when welded and tested in accordance with the corresponding EN ISO specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique not controlled by ITW Welding GmbH.